



Enviro Cleaning Solutions Ltd

Technical Data Sheet

Reference	Graffgo Stable Roof Coating
Purpose	A one pack single coat permanent non-sacrificial coating giving excellent protection against small leaks and cracks to roofs and walls. The product allows easy repair to small holes and cracks with just a brush or roller.
Colour	Clear and Pigmented Liquid
Application	Apply by brush, roller, convention or airless spray.
Volume Solids	82% Matt; 78% Gloss; 48% Pigmented
Recommended Film Thickness	DFT to be determined by Specialist Coatings International depending on substrate and porosity, normally WFT should be 125 microns and DFT 95 microns
Coverage Rate	Theoretical 8 to 10 square metres/litre
Drying Time	Touch dry and protection from rain 2 / 4 hours; full cure 24 hours. Re coating (if required) time 3 to 4 hours
Thinners/Brushwash	Disposal
Weight Per Litre Flash Point	.90-1.02
V.O.C	Above 64deg C. 50 grams per litre
Finish	Semi Matt
Application Temperature	-5DegC +60DegC
Surface Preparation	All surfaces must be clean and dry, remove any soiling with water etc. Any soiling/dust or damp apparent on the surfaces i.e. roof surface/ wood /wooded walls should be cleaned and dried, prior to application. For larger holes and areas a second coat maybe beneficial.

11 The Haven
Hythe, Kent
CT21 4PJ
United Kingdom

Tel: +44(0)1303 265161/07921 949181
Website: www.envirocleaningsolutions.co.uk
Email: jane@envirocleaningsolutions.co.uk
Issue date 05.02.2021